


Coating characteristics of CYTOP

Precautions for handling


Please be sure to read MSDS before using this product to ensure safe handling.

1 Example of spin coating (CTX-809A type, CTL-800A type)

- (1) Coating conditions
- Spin condition: 500 rpm x 5 sec. -> Specified number of revolution x 20 sec.
 - Baking condition: 180 to 200°C x 30 to 60 min.
 - Substrate: Silicon wafer (150mm in diameter (6 inches))
 - Membrane thickness measurement: ULVAC “DEKTAK”
- (2) Diagram showing relation between spinning speed and membrane thickness after drying




* This is a reference value and it does not assure performance.



For *1 and *2, standard part number CTL-816AP was diluted.
 * This is a reference value and it does not assure performance.


2 Example of dip coating (CTX-100AE type, CTL-100AE type)

CTX-100AE dip coating membrane thickness curve
 (The pull-up speed is 60 mm/min.)



* This is a reference value and it does not assure performance.

CTL-100AE dip coating membrane thickness curve
 (The pull-up speed is 60 mm/min.)



* This is a reference value and it does not assure performance.