

# EXCENOL

*Polyols for CASE application*

\* CASE : coating/adhesive/sealant/elastomer

Product	Functionality	Average MW	Properties	
			OH Value (mgKOH/g)	Viscosity(25°C ) (mPa·s at 25°C)
420	2	400	280	70
720	2	700	160	100
1020	2	1,000	112	150
2020	2	2,000	56	310
3020	2	3,200	35	580
430	3	430	400	350
1030	3	1,000	160	250
3030	3	3,000	56	500
4030	3	4,000	42	670
5030	3	5,100	33	910

Note : The values shown above are typical values, not guaranteed values.

The above technical data is correct at time of going to print: 1 November 2014.  
Please contact AGC for further updates and the latest information.  
AGC reserves the right to revise its product range at any time without prior notice.

**AGC CHEMICALS**  
Polyurethanes Division  
Shin-Marunouchi Bldg  
1-5-1, Marunouchi Chiyoda-ku  
TOKYO 100-8405 JAPAN  
Tel: +81-3-3218-5404  
Fax: +81-3-3218-7845  
Email : info-agchp@agc.co.jp  
[www.agc.com](http://www.agc.com)

**AGC CHEMICALS AMERICAS, INC.**  
55 East Uwchlan Avenue,  
Suite 201, Exton PA 19341  
USA  
Tel: +1-610-423-4300  
Fax: +1-610-423-4301  
Email : info-agcchem.com  
[www.agcchem.com](http://www.agcchem.com)

**AGC CHEMICALS EUROPE, LTD.**  
Commercial Centre  
Zuidplein 80  
1077 VX Amsterdam, The Netherlands  
Tel: +31 (0) 20 880 4170  
Fax: +31 (0) 20 880 4188  
Email : enquiries@agcce.com  
[www.agcce.com](http://www.agcce.com)