

EXCENOL

Polyols for Flexible Foams

Product	Average MW	Properties		Application (suitable for)
		OH Value (mgK OH/g)	Viscosity (mPa·s at 25°C)	
230	3,000	56	510	Hot Moulded Foam
820	4,900	34	860	Semi-rigid Foam HR Moulded Foam
828	5,000	34	890	Semi-rigid Foam HR Moulded Foam
837	6,000	27	1,200	Semi-rigid Foam HR Moulded Foam
980	-	445	5,000	Semi-rigid Foam HR Moulded Foam
981	-	445	8,000	Semi-rigid Foam HR Moulded Foam

Note : The values shown above are typical values, not guaranteed values.

The above technical data is correct at time of going to print: 1 November 2014.
Please contact AGC for further updates and the latest information.
AGC reserves the right to revise its product range at any time without prior notice.

AGC CHEMICALS
Polyurethanes Division
Shin-Marunouchi Bldg
1-5-1, Marunouchi Chiyoda-ku
TOKYO 100-8405 JAPAN
Tel: +81-3-3218-5404
Fax: +81-3-3218-7845
Email : info-agchp@agc.co.jp
www.agc.com

AGC CHEMICALS AMERICAS, INC.
55 East Uwchlan Avenue,
Suite 201, Exton PA 19341
USA
Tel: +1-610-423-4300
Fax: +1-610-423-4301
Email : info-agcchem.com
www.agcchem.com

AGC CHEMICALS EUROPE, LTD.
Commercial Centre
Zuidplein 80
1077 VX Amsterdam, The Netherlands
Tel: +31 (0) 20 880 4170
Fax: +31 (0) 20 880 4188
Email : enquiries@agcce.com
www.agcce.com