

Corrosion test data

-Effects on metal- (Corrosion amount [mg/dm² x day] after immersing at boiling point x 3 days)

Metal type	Asahi Klin AK-225	Methylene chloride Super M	Asahi Trichlor AL	Asahi Perchlor Super M
Iron (SPCC-SB)	<0.1	<0.1	<0.1	<0.1
Stainless (SUS304)	<0.1	<0.1	<0.1	<0.1
Magnesium	<0.1	<0.1	<0.1	<0.1
Aluminium	<0.1	<0.1	<0.1	<0.1
Zinc	<0.1	<0.1	<0.1	<0.1
Silver	<0.1	-	-	-
Copper	<0.1	<0.1	<0.1	<0.1
Nickel silver	<0.1	<0.1	<0.1	<0.1
Phosphor bronze	<0.1	<0.1	<0.1	<0.1
Brass	<0.1	<0.1	<0.1	<0.1
Tin	<0.1	<0.1	<0.1	<0.1
Solder	<0.1	<0.1	<0.1	<0.1
Tin-plate	<0.1	<0.1	<0.1	<0.1
Cadmium plating	<0.1	<0.1	<0.1	<0.1
Nickel plating	<0.1	<0.1	<0.1	<0.1
Nickel chromium plating	<0.1	<0.1	<0.1	<0.1
Anodic oxide coating	<0.1	<0.1	<0.1	<0.1

Corrosion data shown below is not guaranteed and is for reference purposes only.

Please carry out test first and confirm that there is no effect.

For detailed corrosion data, see technical materials for each cleaning agent.